



Green Floor Finish GF-165

DESCRIPTION

This product is environmentally preferred zinc and other heavy metals free floor finish. It is user friendly, fast laying, quick drying, and its initial gloss is excellent for use in schools, hospitals, or other high traffic areas where high or low speed buffing without powdering is desired. Synthetic detergents and emulsifiers have little effect on this product's gloss and durability.

INSTRUCTIONS

For best results apply full strength over freshly stripped and rinsed floor. Apply first coat lightly, being more concerned with even coverage than quantity of finish applied. Allow approximately 15 to 20 minutes drying time between coats then apply a second coat a little heavier than the first. Repeat this procedure for up to 4 coats if necessary or desired. Please allow 24 hours cure time after last coat before high speed burnishing; although under some conditions burnishing between coats can be performed if proper care is taken.

FEATURES

- User Friendly
- Complies with CARB and VOC standards
- Meets GreenSeal GS-40
- Zinc free formula

SPECIFICATIONS

Appearance:	White Emulsion	pH:	8.9
Odor:	Low	Biodegradable:	Yes
Specific gravity:	1.03	Durability:	Excellent